

## ROKANATE M PE 2402

<b>CHEMICAL NAME</b>	Prepolymer based on diphenylmethane diisocyanate (MDI)
<b>TECHNICAL REQUIREMENTS</b>	NCO content, % (m/m).....24.0 – 25.0 (PN-EN ISO 14896:2010) Density at 25°C g/ml.....1.16 – 1.18 (PN-EN ISO 3675:2004) Dynamic viscosity at 25°C mPas.....200 – 500 (ASTM D4878-15, met. A)
<b>APPLICATION</b>	Rokanate M PE 2402 is an isocyanate component, used for production of integral polyurethane foam. It can be processed on both low- and high pressure machines.