

## ROKESTER DP 1720.01

<b>CHEMICAL NAME</b>	Polyester polyol
<b>TECHNICAL REQUIREMENTS</b>	Appearance at 25°C .....viscous liquid (visually) Hydroxyl value, mg KOH/g ..... 160 – 180 (PN-EN ISO 2554:2001) Acid value, mg KOH/g .....2.0 – 3.0 (PN-EN ISO 2114:2005, solvent: acetone) Water, % (m/m) .....max. 0.10 (PN ISO 760:2001) Dynamic viscosity at 25°C, mPas .....1500 – 2100 (PN-EN ISO 3219:2000, cone No. 4, rpm 450)
<b>INFORMATIVE DATA*</b>	Density at 25°C, g/ml ..... ~1,23
	* These informative data are not technical requirements and cannot form the basis for any claims.
<b>APPLICATION</b>	Aliphatic-aromatic polyester polyol designed for the for the manufacture of one-component polyurethane foams (OCF).