

ROKOPOL G700

CHEMICAL NAME	Polyether polyol, polyoxyalkylene triol based on glycerol
CAS NUMBER	25791-96-2
TECHNICAL REQUIREMENTS	Appearance at 25°C Homogeneous, clear liquid Hydroxyl value, mg KOH/g 225 – 250 (ASTM D4274-16, met. D) Acid value, mg KOH/g max. 0.10 (ASTM D7253-16, bromothymol blue) Water content, % (m/m).....max. 0.10 (ASTM D4672-18) Colour, Hazen units max. 50 (ASTM D1209-05(2019)) Dynamic viscosity at 25°C, mPas* 220 – 270 (ASTM D4878-15, met. A) * parameter determined on customer's request

GENERAL DATA**	Molecular mass ~700 Density at temp. 25°C, g/ml ~1.030 Flash point, °C..... above 230 Content of Na ⁺ + K ⁺ , mg/l max. 5 <u>Contains BHT free antioxidants</u>
-----------------------	---

**This information data does not constitute technical requirements and cannot be the basis for complaints.

APPLICATION	For the production of rigid polyurethane foams, one-component foams and other polyurethane-based materials.
--------------------	---