

ROKANATE M PE 0201

CHEMICAL NAME	Prepolymer based on diphenylmethane diisocyanate (MDI)
TECHNICAL REQUIREMENTS	NCO content, % (m/m).....1.9 – 2.5 (PN-EN ISO 1242:2013-06)
	Density at 25°C g/ml.....1.06 – 1.09 (PN-EN ISO 3675:2004)
	Dynamic viscosity at 25°C mPas.....8 000 – 13 000 (ASTM D4878-15, met. A)
	Appearance/ colour at 25°C.....liquid, colorless to yellow
APPLICATION	ROKANATE M PE 0201 is a single-component, polyurethane waterproofing membrane used to protect concrete screeds, foundations and walls against moisture. It is moisture curing.