

ROKANATE M PE 0805

CHEMICAL NAME	Prepolymer based on diphenylmethane diisocyanate (MDI)
TECHNICAL REQUIREMENTS	NCO content, % (m/m).....7.9 – 8.6 (PN-EN ISO 1242:2013-06)
	Density at 25°C g/ml.....1.06 – 1.09 (PN-EN ISO 3675:2004)
	Dynamic viscosity at 25°C mPas.....100 – 500 (ASTM D4878-15, met. A)
	Appearance/ colour at 25°C.....liquid, colorless to yellow
APPLICATION	ROKANATE M PE 0805 is one component polyurethane adhesive used in the production of regenerated foam blocks (rebounding foam). It is cured with moisture.