

ROKOPOL MH2016

CHEMICAL NAME Dispersion of styrene acrylonitrile copolymer in reactive oxyalkylated polyol

TECHNICAL REQUIREMENTS

Appearance at 25°Cwhite, opaque liquid

Hydroxyl value, mg KOH/g 25 – 28
(ASTM D4274-16, met. D)

Acid value, mg KOH/g max. 0.1
(ASTM D7253-16, bromothymol blue)

Water content, % (m/m) max. 0.2
(ASTM D4672-18)

Dynamic viscosity at 25°C, mPas*1700 – 2700
(ASTM D4878-15, met. A)

* parameter determined on customer's request

GENERAL DATA***

Density at temp. 25°C, g/ml~1.029

Flash point, °C > 200

Contains BHT free antioxidants

***These informative data are not technical requirements and cannot form the basis for any claims.

APPLICATION For production of High Resilience block and moulded polyurethane foams.