

ROKESTER DP NV 2416.01

CHEMICAL NAME	Polyester polyol
TECHNICAL REQUIREMENTS	Appearance at 25°C homogenous, clear liquid colorless to straw (visually) Hydroxyl value, mg KOH/g 240 – 260 (PN-EN ISO 2554:2001) Acid value, mg KOH/g 1.90 – 2.40 (PN-EN ISO 2114:2005, solvent acetone) Water, % (m/m) max. 0.15 (PN ISO 760:2001) Dynamic viscosity at 25°C, mPas 1000 – 3000 (PN-EN ISO 3219:2000, cone No.4, rpm 300)
INFORMATIVE DATA*	Density at 25°C, g/ml ~1.23
	* These informative data are not technical requirements and cannot form the basis for any claims.
APPLICATION	Aromatic polyester polyol for the production of PUR/PIR foams.