

The product was developed as part of a research and development project co-financed by the European Union from the European Regional Development Fund.

## ROKOPOL iFlex N30

<b>CHEMICAL NAME</b>	Polyether polyol based on renewable raw material
<b>TECHNICAL REQUIREMENTS</b>	Appearance at 25°C ..... Homogeneous, clear liquid Hydroxyl value, mg KOH/g..... 46 – 50 (ASTM D4274-23, met. D) Acid value, mg KOH/g..... max. 0.1 (ASTM D7253-22, bromothymol blue) Water content, % (m/m)..... max. 0.1 (ASTM D4672-24) Dynamic Viscosity at 25°C, mPas* .....750 – 1050 (ASTM D4878-23, met. A)
	*parameter determined on customer's request
<b>INFORMATIVE DATA**</b>	Density at temp. 25°C, g/ml .....~1.020 Flash point, °C..... > 250 Contains BHT free antioxidants.
	**These informative data are not technical requirements and cannot form the basis for any claims.
<b>APPLICATION</b>	For production slabstock polyurethane foams with wide range density end very good resistance to “scorch”.