

TSP

CHEMICAL NAME	Styrenated phenol
EC NUMBER	701-171-0
TECHNICAL REQUIREMENTS	Appearance: yellow viscous liquid
	Styrenated phenol, %m/m min 93,0
	Styrene, %m/m max 0,05
	Phenol, %m/m max 1,5
	Monostyrenated phenol, %m/m max 2,0
	Distyrenated phenol, %m/m 10 - 30
	Tristyrenated phenol, %m/m 65 - 80
	Tetrastyrenated phenol, %m/m max 5,0
	Dimer styrene, %m/m max 7,0
GENERAL DATA	-
APPLICATION	TSP is used as an intermediate for the production mainly of surfactants