

# ROKESTER DP NV 2402.01

<b>CHEMICAL NAME</b>	Polyester polyol
<b>TECHNICAL REQUIREMENTS</b>	<p>Appearance at 25°C.....homogenous liquid colorless to olive (visually)</p> <p>Hydroxyl value, mg KOH/g.....230 – 250 (PN-EN ISO 2554:2001)</p> <p>Acid value, mg KOH/g.....1.50 – 2.50 (PN-EN ISO 2114:2005, solvent: acetone)</p> <p>Water, % (m/m).....max. 0.15 (PN-ISO 760:2001)</p> <p>Dynamic viscosity at 25°C, mPas .....max 5 000 (PN-EN ISO 3219:2000, cone No.4, rpm 180)</p>
<b>INFORMATIVE DATA*</b>	<p>Density at 25°C, g/ml ..... ~1.23</p> <p>* These informative data are not technical requirements and cannot form the basis for any claims.</p>
<b>APPLICATION</b>	Specialized polyester polyol intended for applications in PUR/PIR foams..