

## ACTIVE PLAY AS H 8013\_2

<b>CHEMICAL NAME</b>	Prepolymer based on diphenylmethane diisocyanate (MDI).
<b>TECHNICAL REQUIREMENTS</b>	<p>NCO content, % (m/m)..... 14.5 – 15.5 (PN-EN ISO 14896:2010)</p> <p>Density at 25°C, g/ml.....1.17 – 1.19 (PN-EN ISO 3675:2004)</p> <p>Dynamic viscosity at 25°C, mPa·s .....1000 – 2000 (ASTM D4878-15, met. A)</p> <p>Appearance/ colour at 25°C..... liquid, dark amber</p>
<b>APPLICATION</b>	<p>One-component polyurethane adhesive contains no organic solvents and have very good flexibility of the joint.</p> <p>ACTIVE PLAY AS H 8013_2 is used for the manufacture of molded elements on cold and hot from granulated rubber SBR or EPDM.</p> <p>ACTIVE PLAY AS H 8013_2 is used as a binder for the production of safety surfaces, such as tiles for playgrounds, fitness room, gym and similar products made of SBR and EPDM rubber granules.</p>