

Si-PolyU 2550

Product Description

Si-PolyU 2550 is an apolar, moderate viscous polymer, designed for solvent- and isocyanate free sealants and elastic adhesives formulations. It has a polypropylene oxide-backbone, terminated with trimethoxysilyl groups.

The polymer cures at ambient temperatures upon reaction with water. Formulations based on this polymer show good adhesion properties to various substrates, without prior use of primers or any surface treatment.

Technical Data

(No Specification)

Product Properties	Technical Data
Appearance at 23°C	clear, colorless to yellowish liquid
Density at 23°C	~ 1.01 g/cm ³
pH	6-8
Viscosity Brookfield RV, SC4-31 Spindle, 3 RPM, 25°C, 20 min	45 000 – 70 000 mPa•s

Properties and Applications

Si-PolyU 2550 is a hybrid polymer, which is used as reactive binder in adhesives, sealants or coatings.

Handling and Storage

Si-PolyU 2550 should be stored under dry and cool conditions. Freezing and exposure to direct sunlight of the product should be avoided.

The 'Best use before end' date of each batch is shown on the product label.

When stored as recommended, the shelf-life is 12 months.

Si-PolyU 2550 reacts upon exposure to moisture. Thus, it is recommended to tightly close container after use. Opened containers should be consumed soon.

December 2022

This technical data sheet is provided to the best of our knowledge for informational purposes only. However, to the extent permitted by law, the information does not constitute a guarantee, commitment or liability on the part of PolyU nor does it exempt the user from conducting its own investigations and tests. In particular, they do not exempt the user from testing our products for their suitability for the intended processes and purposes. Any legal claims of third parties must be observed.

PolyU GmbH • Otto-Roelen-Str. 3 • 46147 Oberhausen • Germany • Phone +49 (0)208 387 649 0 • info@polyu.eu